



## 产品说明

## BAEROPAN SMS 635 R

<b>名称</b>	铅盐复合稳定剂，片状	
<b>Definition</b>	Lead stabilizer/lubricant one-pack, flake	
<b>指标</b>	铅含量：约 20%	Pb content: Approximately 20%
<b>Properties</b>	灰分含量：43.4 ± 1.5%	Ash content: 43.4 ± 1.5%
<b>特性</b>	BAEROPAN SMS 635 R 是经济型的铅盐复合稳定剂，具有良好的润滑性能和优异的热稳定性，适用于管材挤出相关的应用。	
<b>Features</b>	BAEROPAN SMS 635 R is an economical basic lead stabilizer/lubricant one pack with well-adjusted lubrication and good thermo-stability for the extrusion of pipes.	
<b>性能</b>	BAEROPAN SMS 635 R 具有宽阔的加工范围，使用常用的挤出机、PVC 树脂、填料都能达到很高的生产效率。	
<b>Performance</b>	This non-dusting compound can be used under a wide range of processing conditions and allows high production rates with most common extruders, PVC types and fillers. 建议使用量为 2.5 - 3.0 phr. Recommended dosage: 2.5 - 3.0 phr. 为使 BAEROPAN SMS 635 R 均匀分散，制备干混料时需高速搅拌并且要达到 90℃ 以上。 In order to obtain a homogeneous dispersion of BAEROPAN SMS 635 R it is necessary to prepare the dry blend in high-speed mixer at elevated temperature, above 90°C.	
<b>质量控制</b>	先进的现代化生产工艺保证产品质量、品质的稳定性。	
<b>Quality control</b>	A modern, state-of-the-art plant process with strict control ensures consistent quality in chemical and physical properties.	
<b>储存</b>	常温下干燥保存，如果打开使用，请注意密封。	
<b>Storage</b>	Storage in dry areas at normal ambient temperatures is recommended. Open containers of unused product should be firmly closed for storage.	

NOTICE: Although the information and recommendations contained in this document (hereinafter "Information") are presented in good faith and believed to be correct at the date of their publication, BAERLOCHER makes no representations or warranties as to the completeness or accuracy of Information.

Information is supplied upon the condition that the persons or entities receiving same will make their own determination as to its suitability for their purposes prior to their use. In no event, will BAERLOCHER be responsible or liable for any loss of profits, lost goodwill, direct, special, indirect, incidental, or consequential damages of any nature whatsoever, including without limitation lost revenue, resulting from the use of or reliance upon Information or the product to which Information refers.

Nothing contained in this disclaimer is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent or intellectual property right, and BAERLOCHER makes no representation or warranty, express or implied, that the use thereof will not infringe any patent or intellectual property rights.

No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which Information refers.

### Baerlocher Plastic Additives (Jiangsu) Co., Ltd

5 Xingfeng Road  
Xinbei Zone, Changzhou  
Jiangsu, China 213033

Tel: 86-519-81196690  
Tax: 86-519-81189971  
www.baerlocher.com