



产品说明

BAEROPAN SMS 318

名称	铅盐复合稳定剂，片状
Definition	Lead stabilizer/lubricant one-pack, flake
指标	铅含量：约 26% Pb content: Approximately 26%
Properties	灰分含量：44.6 ± 1.5% Ash content: 44.6 ± 1.5%
特性	BAEROPAN SMS 318 是标准型的铅盐复合稳定剂，具有良好的润滑性能和优异的热稳定性，适用于管材挤出相关的应用。
Features	BAEROPAN SMS 318 is a standard basic lead stabilizer/lubricant one pack with well-adjusted lubrication and good thermo-stability for the extrusion of pipes.
性能	BAEROPAN SMS 318 具有宽阔的加工范围，使用常用的挤出机、PVC 树脂、填料都能达到很高的生产效率。
Performance	This non-dusting compound can be used under a wide range of processing conditions and allows high production rates with most common extruders, PVC types and fillers. 建议使用量为 2.5 - 3.0 phr. Recommended dosage: 2.5 - 3.0 phr. 为使 BAEROPAN SMS 318 均匀分散，制备干混料时需高速搅拌并且要达到 90°C 以上。 In order to obtain a homogeneous dispersion of BAEROPAN SMS 318 it is necessary to prepare the dry blend in high-speed mixer at elevated temperature, above 90°C.
质量控制	先进的现代化生产工艺保证产品质量、品质的稳定性。
Quality control	A modern, state-of-the-art plant process with strict control ensures consistent quality in chemical and physical properties.
储存	常温下干燥保存，如果打开使用，请注意密封。
Storage	Storage in dry areas at normal ambient temperatures is recommended. Open containers of unused product should be firmly closed for storage.